

QUICK PATCH[®]

UV TECHNOLOGY

Product Data: Quick Patch UV Light activated repair patch.

Product Data

Appearance	Sheet Lamination
Color	Grey
Curing Mechanism	Ultra Violet (UV), Natural or UV Lamp
Material Thickness	1.7-1.9 mm. (can also be supplied in 1.0-1.5 mm range)
Weight	2.9 kg/m ²

Technical Data

Test Methods

Tensile strength: > 55 MPa	BS 2782 bis 1994
Flexural strength: >130 MPa	ASTM D 790-03
Flexural modulus: >5,98 MPa	ASTM D 2344
Elongation at break: >3%	BS 2782 bis 1994
Coeff. of thermal expansion: $2,9 \cdot 10^{-5} K^{-1}$	ASTM D 696-03
Impact Resistance: >60 kJ/m ²	BS EN ISO 180
Hardness: >60 Barcol	ASTM D 2583
Compressive strength: >200 MPa	ASTM D 695-2002
Adhesion to C-steel: >14 MPa	ASTM D4541-02
Water vapour permeability: 0,28 g/m ² /24h/mmHg	ASTM E 96
Heat distortion: >145°C	ASTM D 648
Fire rating: Class 1	BS 476 pt7:1997 ASTM 84
Flash point: >32°C	ASTM D 93

Electrical Properties

Test Methods

Dielectric strength: 9 kV/mm	IEC 243
Arc resistance: >180 sec.	ASTM D 495
Tracking resistance: >600 V	IEC 112
Insulation resistance: 10 to the power of 13 ohms	IEC 93

Physical - chemical properties

Heat Resistance:	Wet – 90° C Dry – 200° C
Chemical resistance:	Good. Chemical resistance chart available upon request.

All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the user's responsibility to satisfy themselves with their own testing to determine suitability of the product for their own intended use, application and job situation. User assumes all risk and liability resulting from their use of product. We do not suggest or guarantee that any hazard listed herein is the only one which may exist. Neither seller, nor manufacturer, shall be liable to the buyer or any third party for any injury, loss or damage directly or indirectly resulting from use of, or inability to use the product. Recommendations or statements, whether in writing or oral, other than those contained herein are not binding upon the manufacturer, unless in writing and signed by a corporate officer of the manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and Bullseye Products LLC makes no claim that these tests or any other tests accurately represent all environments.

 **BULLSEYE**
PRODUCTS
www.BullseyeProductsUSA.com

3595 Polaris Ave, Las Vegas, NV 89103
302-231-2624
BullseyeProductsllc@yahoo.com